

ZEISS OPHTHALIN

Technical Specifications



Seeing beyond

OPHTHALIN®	
Behavior	Viscous-cohesive
Substance	Sodium Hyaluronate
Concentration I (%)	1.2
Concentration II (mg/ml)	12
Volume (ml)	0.8
Osmolality (mOsmol/kg)	288 – 352
Molecular weight (megadalton ¹)	1.8 – 2.2
Zero-shear viscosity (Pa s ²)	105
Cannula	27 G
Storage temperature (°C)	2–8
Single pack content:	1 x intracameral syringe, 1 x 27 G cannula

ZEISS OPHTHALIN is latex and phthalate free, has a shelf life of 3 years and a pH value of 7.2.

¹ Megadalton = 1 million Dalton

² Pa s = 1000 mPa s





Manufactured by:

Anika Therapeutics, Inc.
32 Wiggins Avenue
Bedford, MA 01730
United States of America



Distributed in USA by:

Carl Zeiss Meditec, Inc.
5300 Central Parkway
Dublin, CA 94568
United States of America

**Privat label manufacturer
and distributor in Canada:**

Carl Zeiss Canada Ltd.
45 Valleybrook Drive
Toronto, ON M3B 2S6
Canada
www.zeiss.com/ovd
www.zeiss.com/contact