

ZEISS TWINVISC

Technical Specifications



Seeing beyond

	First chamber: Dispersive	Second chamber: Cohesive
Behavior	Medium-viscosity dispersive	Viscous-cohesive
Origin	Bacterial fermentation	Bacterial fermentation
Substance	Sodium Hyaluronate	Sodium Hyaluronate
Concentration I (%)	2.2	1.0
Concentration II (mg/ml)	22	10
Volume (ml)	0.7	0.7
CDI	26	36
Osmolality (mOsmol/kg)	300 – 360	300 – 350
Molecular weight (megadalton ¹)	1.0	2.1
Pseudoplasticity	8	18
Zero-shear viscosity (Pa s ²)	14	18
Cannula	25 G	25 G
Storage temperature (°C)	2 – 8	2 – 8
Content:	1 × two-chamber intracameral syringe, 1 × 25 G cannula	

TWINVISC® is latex and phthalate free, has a shelf life of 2 years and a pH range between 6.8 and 7.6.

¹ Megadalton = 1 million Dalton

² Pa s = 1000 mPa s



CE 0344

TWINVISC



Hyaltech Ltd.

Starlaw Business Park
Livingston EH54 8SF
United Kingdom
www.zeiss.com/ovd
www.zeiss.com/contact



Carl Zeiss Meditec AG

Goeschwitzer Str. 51–52
07745 Jena
Germany
www.zeiss.com/ovd
www.zeiss.com/contact

en-OUS_32_022_01381 Printed in Germany. CZ-IX/2021 International edition: Only for sale in selected countries.
The contents of the brochure may differ from the current status of approval of the product or service offering in your country. Please contact our regional representatives for more information. Subject to changes in design and scope of delivery and due to ongoing technical development.
TWINVISC is a registered trademark of Carl Zeiss Meditec AG or other companies of the ZEISS Group in Germany and/or other countries.
© Carl Zeiss Meditec AG, 2021. All rights reserved.