

ZEISS Z-HYALIN

ZEISS Z-HYALIN plus

Technical Specifications



Seeing beyond

	Z-HYALIN®	Z-HYALIN® plus
Behavior	Viscous-cohesive	Viscous-cohesive
Origin	Bacterial fermentation	Bacterial fermentation
Substance	Sodium Hyaluronate	Sodium Hyaluronate
Concentration I (%)	1.0	1.5
Concentration II (mg/ml)	10	15
Volume (ml)	1.0	1.0
CDI	39	44
Osmolality (mOsmol/kg)	300 – 350	300 – 360
Molecular weight (megadalton ¹)	2.9	2.9
Pseudoplasticity	75	133
Zero-shear viscosity (Pa s ²)	72	295
Cannula	27 G	27 G
Storage temperature (°C)	2–8	2–8
Singlepack content:	1 × intracameral syringe, 1 × 27 G cannula	1 × intracameral syringe, 1 × 27 G cannula
Multipack content:	10 × intracameral syringes, 10 × 27 G cannulas	10 × intracameral syringes, 10 × 27 G cannulas

Z-HYALIN and Z-HYALIN plus are latex and phthalate free, have a shelf life of 3 years and a pH range between 6.8 and 7.6.

¹ Megadalton = 1 million Dalton

² Pa s = 1000 mPa s



CE 0344

Z-HYALIN
Z-HYALIN plus



Hyaltech Ltd.

Starlaw Business Park
Livingston EH54 8SF
United Kingdom
www.zeiss.com/ovd
www.zeiss.com/contact



Carl Zeiss Meditec AG

Goeschwitzer Str. 51–52
07745 Jena
Germany
www.zeiss.com/ovd
www.zeiss.com/contact

en-OUS_32_022_014211 Printed in Germany. CZ-XI/2021 International edition: Only for sale in selected countries.
The contents of the brochure may differ from the current status of approval of the product or service offering in your country. Please contact our regional representatives for more information. Subject to changes in design and scope of delivery and due to ongoing technical development. Z-HYALIN and Z-HYALIN plus are registered trademarks of Carl Zeiss Meditec AG or other companies of the ZEISS Group in Germany and/or other countries.
© Carl Zeiss Meditec AG, 2021. All rights reserved.